

TITLE OF THE INVENTION

SHEET-FORM, CURABLE PRESSURE-SENSITIVE ADHESIVE

BACKGROUND OF THE INVENTION

FIELD OF THE INVENTION

5 The present invention relates to a sheet-form, curable
pressure-sensitive adhesive, and more particularly to a
sheet-form, curable pressure-sensitive adhesive which is
sufficiently tacky to be adhered to an adherend and also has
the ability to cure upon application of an activation energy
10 thereto, either before or after the adherend is combined
with another adherend therethrough.

BACKGROUND ART

Acrylic pressure-sensitive adhesives have been widely
used in a variety of pressure-sensitive adhesive-carrying
15 products including pressure-sensitive adhesive tapes due to
their excellent properties such as resistance to heat,
environment and oils. The general design of such acrylic
pressure-sensitive adhesives controls their elastic modulus
to a reduced level to develop pressure-sensitive adhesive
20 strength thereof. Accordingly, acrylic pressure-sensitive
adhesives, in turn, are difficult to develop their adhesive
strength to a higher level as regular adhesives exhibit.
This prevents their use in applications requiring a high
joint strength, as for joining steels for vehicles, housing
25 or building structural members, or casing members.

Under such circumstances, a curable pressure-sensitive adhesive has been proposed which provides a good operational characteristics and is safe due to absence of volatile contents while capable of providing high levels of joint strength and film toughness as comparable to those of regular adhesives. For example, Japanese Patent Laying-open No. Hei 2-272076 discloses an adhesive tape which utilizes a curable pressure-sensitive adhesive having a composition containing an acrylate monomer and an epoxy resin. Among the photopolymerizable compositions, the acrylate monomer alone is polymerized to provide the pressure-sensitive adhesive tape. For the purpose of enhancing its adhesion strength, the epoxy resin is heat cured after the pressure-sensitive adhesive tape is adhered to an adherend.

However, the method disclosed in the Japanese Patent Laying-open No. Hei 2-272076 utilizes heat for curing the epoxy resin. This prevents the use of materials having a poor heat resistance as the adherend, resulting in imposing limitations upon material selection of the adherend.

Japanese Patent Kohyo No. Hei 5-506465 discloses a pressure-sensitive adhesive which has a composition including a radically photopolymerizable component such as an acrylate monomer, cationically photopolymerizable component such as an epoxy compound and an organometallic complex salt polymerization initiator. This pressure-

10059136-013102
sensitive adhesive has been proposed in an attempt to
enhance tackiness thereof. Both of radical and cationic
photopolymerizations proceed during the stages of
manufacturing said pressure-sensitive adhesive and complete
5 by the time when the pressure-sensitive adhesive is formed
into a sheet form. That is, an adequate strength has been
given to the thus obtained pressure-sensitive adhesive
before it is adhered to an adherend. Accordingly, while the
pressure-sensitive adhesive is sufficiently tacky to adhere
10 to the adherend, the application of an external stimulation
such as heat or radiation thereto contributes no further
improvement in adhesion strength.

On the other hand, epoxy resin adhesives exhibit
excellent physical and chemical properties including creep
15 resistance, light resistance, water resistance, heat
resistance and chemical resistance. In addition, they
provide high adhesion strength and have the ability to
adhere to a wide range of materials such as metals, plastics
and glasses. All of the above have led to a wide-spread use
20 of the epoxy resin adhesives when joining various material
members each other.

However, the general use of those epoxy resin adhesives
in liquid form disadvantageously results in uneven coating
and edge flowing derived from excessive application thereof
25 to provide a poor appearance at joint interface edges, and

prevents repeated application thereof onto once applied surface. Also, the typical epoxy resin adhesives are of two-part type so that a mixing ratio of a base resin to a curing agent is limited to a narrow range. Accordingly,
5 care must be taken in order to mix them in appropriate proportions. The failure to do so is likely to prevent the prepared adhesives from exhibiting a purposed adhesive strength.

In view of the above, a proposal has been made to
10 provide a sheet-form epoxy resin adhesive wherein the epoxy resin adhesive is formed into a sheet or film (Japanese Patent Laying-open No. Sho 60-173076). A sheet-form epoxy resin adhesive however has a high elastic modulus in its ordinary state to exhibit a low initial tackiness. This
15 causes problems that the sheet-form epoxy resin adhesive is unable to provide adequate tackiness and satisfactory operational characteristics when joining adherends. Furthermore, the insufficient adherence thereof to an adherend is inevitably followed by severe conditions such as
20 an elevated temperature and/or pressing under high-pressure to insure complete adhesion to the adherend. Such severe processing conditions prohibit the application of the disclosed adhesive to otherwise tolerable adherends.

SUMMARY OF THE INVENTION

25 An object of the present invention is to provide a

sheet-form, curable pressure-sensitive adhesive which has an adequate initial tackiness, and is capable of being cured upon application of an activation energy thereto and also of being used for joining members having insufficient heat resistances while eliminating the necessities of additional severe conditions such as an elevated temperature and/or pressing under high pressure when applied to an adherend.

Another object of the present invention is to provide a method for joining members which utilizes the above sheet-form, curable pressure-sensitive adhesive.

In accordance with the present invention, a sheet-form, curable pressure-sensitive adhesive is provided which comprises a composition including (A) a high molecular weight polymer, (B) a compound containing an epoxy group and (C) a polymerization initiator which, when an activation energy is applied thereto, initiates the compound (B) to undergo a ring-opening polymerization. In the sheet-form, curable pressure-sensitive adhesive, the high molecular weight polymer (A) has an adequate initial cohesive strength and is sufficiently tacky to readily adhere to an adherend. Also, the application of the activation energy activates the polymerization initiator (C) which causes the ring-opening polymerization of the compound (B) to take place. As a result, the sheet-form adhesive is cured to provide a satisfactory adhesion strength.

Furthermore, since the curing caused by application of the energy does not progress rapidly, the adequate tackiness of the sheet-form, curable pressure-sensitive adhesive enables an easy adherence thereof to the adherend even after the energy application.

The present invention is explained in more detail below.

The High Molecular Weight Polymer (A)

The high molecular weight polymer (A) used in the present invention is added to provide the sheet-form, curable pressure-sensitive adhesive with tackiness in its ordinary state. Any high molecular weight polymers may be used as the polymer (A), as long as they have the ability to impart tackiness and are sufficiently compatible with the compound (B) and the polymerization initiator (C).

Examples of the high molecular weight polymer (A) include acrylic polymers, polyesters, polyurethanes, silicones, polyethers, polycarbonates, poly(vinyl ether)s, poly(vinyl chloride)s, poly(vinyl acetate)s, ethylene-vinyl acetate copolymers, polyisobutylene. Of the above, acrylic polymers are preferably used since they have the ability to utilize a radical photopolymerization reaction as described hereinafter, the excellent compatibility with the compound (B) containing an epoxy group, the excellent tack properties and the others.

Although any particular limitations are not imposed upon a molecular weight of the above high molecular weight polymer, it preferably has a relatively higher molecular weight. The preferred high molecular weight polymer has a weight average molecular weight of from 0.2 millions to 5 millions. If the weight average molecular weight is below 0.2 millions, the cohesive strength of the sheet-form, curable pressure-sensitive adhesive is reduced to possibly cause webbing or peeling when applied. If the weight average molecular weight exceeds 5 millions, an increase in viscosity of the composition including the high molecular weight polymer and the compound containing an epoxy group is caused to possibly prevent sheet-forming of the composition.

The high molecular weight polymer can have various structures, examples of which include, but not limited to, a monopolymer structure, a random copolymer structure, a block copolymer structure, an alternating copolymer structure, a stereoregular structure, a multi-branched structure, a multi-armed structure, a star structure, a tree structure, a ladder structure, a cyclic structure, a helix structure and the others.

As described above, preferable for use as the high molecular weight polymer are acrylic polymers. Among the acrylic polymers, a copolymer obtainable by copolymerizing a compound containing a (meth)acryloyl group with a

copolymerizable monomer copolymerizable therewith is more preferred.


Examples of such compound containing a (meth)acryloyl group include methyl (meth)acrylates, ethyl (meth)acrylates, 5 n-butyl (meth)acrylates, tert-butyl (meth)acrylates, 2-ethylhexyl (meth)acrylates, cyclohexyl (meth)acrylates, n-octyl (meth)acrylates, isooctyl (meth)acrylates, isononyl (meth)acrylates, isomyristyl (meth)acrylates, isobornyl (meth)acrylates, benzyl (meth)acrylates.

10 The term "(meth)acrylates" as used herein is intended to mean "acrylate" or "methacrylate".


More preferable for use as the compound containing a (meth)acryloyl group is a compound which contains at least one (meth)acryloyl group and at least one hydroxyl group per 15 molecule. Illustrative of such a compound containing one or more (meth)acryloyl groups and one or more hydroxyl groups per molecule are 2-hydroxyethyl (meth)acrylates, 3-hydroxypropyl (meth)acrylates, 2-hydroxypropyl (meth)acrylates, 4-hydroxybutyl (meth)acrylates, 2-20 hydroxybutyl (meth)acrylates, 5-hydroxypentyl (meth)acrylates, 6-hydroxyhexyl (meth)acrylates, 3-hydroxy-3-methylbutyl (meth)acrylates, 2-hydroxy-3-phenoxypropyl (meth)acrylates, pentaerythritol tri(meth)acrylates, 2-[(meth)acryloyloxy]ethyl-2-hydroxyethyl phthalic acids, 2-25 [(meth)acryloyloxy]ethyl-2-hydroxypropyl phthalic acids, and

the following compounds (1) through (10):


【Compound 1】




5 【Compound 2】




【Compound 3】




【Compound 4】




【Compound 5】




【Compound 6】




15 【Compound 7】




【Compound 8】



20 【Compound 9】



【Compound 10】



of the above, the compounds (1) through (10) as above-
specified by structural formulas are preferably used since
they are capable of imparting a high level of adhesiveness
to the resulting sheet-form, curable pressure-sensitive
adhesive.

Any compounds can be used as the above copolymerizable
monomer, as long as they have an unsaturated bond to be
copolymerizable with the compounds containing a
(meth)acryloyl group. For the purpose of enhancing storage
stability of the sheet-form, curable pressure-sensitive
adhesive, the use of a compound which is non-reactive with
the epoxy group contained in the sheet-form, curable
pressure-sensitive adhesive is preferred.

In view of the above, it is not preferred to use, as
the copolymerizable monomer, vinyl monomers having an acid
anhydrous skeleton which include carboxyl-containing vinyl
monomers such as acrylic acid and methacrylic acid, and
maleic anhydrides.

Examples of applicable copolymerizable monomers include
methyl (meth)acrylates, ethyl (meth)acrylates, propyl
(meth)acrylates, n-butyl (meth)acrylates, tert-butyl
(meth)acrylates, cyclohexyl (meth)acrylates, 2-ethylhexyl
(meth)acrylates, n-octyl (meth)acrylates, isooctyl
(meth)acrylates, isononyl (meth)acrylates, isomyristyl

(meth)acrylates, stearyl (meth)acrylates, isobornyl
(meth)acrylates, benzyl (meth)acrylates, 2-butoxyethyl
(meth)acrylates, 2-phenoxyethyl (meth)acrylates, glycidyl
(meth)acrylates, tetrahydrofurfuryl (meth)acrylates,
5 hexandiol di(meth)acrylates, ethylene glycol
di(meth)acrylates, polyethylene glycol di(meth)acrylates,
propylene glycol di(meth)acrylates, polypropylend glycol
di(meth)acrylates, neopentyl glycol di(meth)acrylates,
trimethylolpropane tri(meth)acrylates, pentaerythritol
10 di(meth)acrylates, pentaerythritol tri(meth)acrylates,
pentaerythritol tetra(meth)acrylates, dipentaerythritol
hexa(meth)acrylates, epoxy acrylates, polyester acrylates,
urethane acrylates,

【Compound 11】

15 $\text{CH}_2=\text{CH}\cdot\text{C}(\text{O})\text{O}\cdot(\text{CH}_2\text{CH}_2\text{O})_n\cdot\text{CH}_3$ (n=1-10)

【Compound 12】

$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{C}(\text{O})\text{O}\cdot(\text{CH}_2\text{CH}_2\text{O})_n\cdot\text{CH}_3$ (n=1-30)

【Compound 13】

$\text{CH}_2=\text{CH}\cdot\text{C}(\text{O})\text{O}\cdot[\text{CH}_2\text{CH}(\text{CH}_3)\text{O}]_n\cdot\text{CH}_3$ (n=1-10)

20 【Compound 14】


$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{C}(\text{O})\text{O}\cdot[\text{CH}_2\text{CH}(\text{CH}_3)\text{O}]_n\cdot\text{CH}_3$ (n=1-10)

【Compound 15】

$\text{CH}_2=\text{C}(\text{CH}_3)\cdot\text{C}(\text{O})\text{O}\cdot(\text{CH}_2\text{CH}_2\text{O})_n\cdot[\text{CH}_2\text{CH}(\text{CH}_3)\text{O}]_m\cdot\text{CH}_3$

(n=1-10, m=1-10)

【Compound 16】



$$(n=1-10, m=1-10)$$

(meth)acrylonitrile, N-vinylpyrrolidone, N-acryloyl-
5 morpholine, N-vinylcaprolactone, N-vinylpiperidine, styrene,
indene, α -methylstyrene, p-methylstyrene, p-chlorostyrene,
p-chloromethyl styrene, p-methoxy styrene, p-tert-
butoxystyrene, divinylbenzene, vinyl acetates, vinyl
propionate, vinyl butyrates, vinyl caproates, vinyl
10 benzoates, and vinyl cinnamates. These compounds may be
used alone or in any combinations thereof.

Preferable for use as the copolymerizable monomer are
methyl (meth)acrylates, ethyl (meth)acrylates, cyclohexyl
(meth)acrylates, benzyl (meth)acrylates, glycidyl
15 (meth)acrylates, tetrahydrofurfuryl (meth)acrylates, or
(meth)acrylic esters having a C-O-C ether bond such as the
compounds (11) through (16) as above-specified by structural
formulas, since they have relatively higher levels of
cohesion.

20 Also, more preferable for use as the high molecular
weight polymer is a copolymer obtainable by copolymerizing a
compound containing at least one (meth)acryloyl group and at
least one hydroxyl group per molecule with the above
copolymerizable monomer, which enables a shortened cure
25 complete period from energy application till reaching a

maximum adhesive strength and an enhanced adhesive strength.

Still more preferably, as the high molecular weight polymer, acrylic polymer is used which is obtainable by radically photopolymerizing a photopolymerizable composition containing acrylic monomers. In such a case, the photopolymerizable composition is irradiated with a light to yield the acrylic polymer via the radical photopolymerization. It follows that incorporation of the above monomer component and radical photopolymerization initiator in the photopolymerizable composition, together with the compound (A) containing an epoxy group and the polymerization initiator (C), enables readily obtaining the sheet-form, curable pressure-sensitive adhesive in accordance with the present invention by irradiating a sheet comprising the photopolymerizable composition with a light.

The Compound (B) Containing an Epoxy Group

The compound (B) containing an epoxy group for use in the sheet-form, curable pressure-sensitive adhesive of the present invention is utilized to undergo a ring-opening polymerization with the aid of the action of the polymerization initiator which, when an activation energy is applied thereto, induces the ring-opening polymerization of the epoxy linkages to take place, and thereby to cure the sheet-form, curable pressure-sensitive adhesive.

Any compounds which have an epoxy group may be used as

the above compound containing an epoxy group. Examples of the compound containing an epoxy group include epoxy resins such as bisphenol A type epoxy resins, bisphenol F type epoxy resins, novolak type epoxy resins and alicyclic aliphatic epoxy resins; glycidyl ester type compounds; and glycidyl amine type compounds.

The Vinyl Ether Compound

Preferably, the sheet-form, curable pressure-sensitive adhesive in accordance with the present invention further contains the vinyl ether compound. The cationic polymerization of the vinyl ether compound predominantly progresses relative to the ring-opening polymerization of the compound (B) containing an epoxy group. Accordingly, such additional incorporation of the vinyl ether compound is effective in delaying the polymerization of the compound (B) containing an epoxy group, where irradiation of a light as an activation energy activates the polymerization initiator (C) to cause the ring-opening polymerization of the compound (B) to subsequently take place so that the sheet is cured. Furthermore, the adequate tackiness is given to the sheet-form, curable pressure-sensitive adhesive in an early stage after irradiation by the light, since an elastic modulus of the vinyl ether compound is substantially lower than that of the compound containing an epoxy group. These enable an enhanced degree of tackiness of the sheet-form, curable

pressure-sensitive adhesive to an adherend and an extended period from energy application till application to the adherend, i.e., an extended pot life.

Examples of the vinyl ether compound include, but not limited to, n-propyl vinyl ethers, n-butyl vinyl ethers, isobutyl vinyl ethers, tert-butyl vinyl ethers, tert-amyl vinyl ethers, cyclohexyl vinyl ethers, 2-ethylhexyl vinyl ethers, dodecyl vinyl ethers, octadecyl vinyl ethers, 2-chloroethyl vinyl ethers, ethylene glycol butyl vinyl ethers, triethylene glycol methyl vinyl ethers, (4-ninyloxy)butyl benzoates, ethylene glycol divinyl ethers, diethylene glycol divinyl ethers, triethylene glycol divinyl ethers, tetraethylene glycol divinyl ethers, butane-1,4-diol-divinyl ethers, hexane-1,6-diol-divinyl ethers, cyclohexane-1,4-dimethanol-divinyl ethers, (4-vinyloxy)butyl isophthalates, di(4-vinyloxy)butyl glutarates, di(4-vinyloxy)butyl succinates, trimethylol propane trivinyl ethers, 2-hydroxyethyl vinyl ethers, 4-hydroxybutyl vinyl ethers, 6-hydroxyhexyl vinyl ethers, cyclohexane-1,4-dimethanol-monovinyl ethers, diethylene glycol monovinyl ethers, 3-aminopropyl vinyl ethers, 2-(N,N-diethylamino)ethyl vinyl ethers, urethane vinyl ethers, and polyester vinyl ethers. The above vinyl ether compounds may be used in any combinations thereof.

The Polymerization Initiator (C)

205059136-013102
In the sheet-form, curable pressure-sensitive adhesive
in accordance with the present invention, the polymerization
initiator (C) is utilized which is activated upon
application of the activation energy thereto, for the
5 purpose of causing the compound (B) containing an epoxy
group to undergo the ring-opening polymerization. Any types
of initiators may be selected as the polymerization
initiator, as long as they are capable of inducing the ring-
opening polymerization of the compound (B) containing an
10 epoxy group to take place. Such initiators include thermal
polymerization initiators which are activated upon
application of heat energy thereto, and photopolymerization
initiators which are activated when irradiated with a light.
In particular, cationic photopolymerization initiators are
15 preferably used due to their applicability to adherends
having a poor heat resistance.

As the thermal polymerization initiators, any
suitable polymerization initiators may be utilized which
have the ability to be activated upon application of heat to
20 cause the compound (B) containing an epoxy group to undergo
the ring-opening polymerization. Illustrative of such
initiators are dicyandiamides, hydrazides, imidazole
compounds, amine adducts, amine imides, sulfonium salts,
ammonium salts, pyridinium salts and the like.

25 Any initiators which are capable of causing the epoxy

linkages to undergo the ring-opening polymerization when irradiated with a light may be useful for the photopolymerization initiators. For example, photo-sensitive onium salts or organometallic complexes can be suitably utilized.

The photo-sensitive onium salts are preferably used as the above cationic photopolymerization initiator. That is, the photo-sensitive onium salts are suitable for use as the compounds which can be activated when irradiated with an ultraviolet light in the preferable wavelength range above 300 nm which has a sufficiently high energy strength to effect a rapid progress of ring-opening of the epoxy linkages.

In an exemplary case where the photopolymerizable composition is irradiated with a light to yield tack polymers via the radical photopolymerization, the radiation preferably has a wavelength of at least 370 nm. In such a case, the radiation must be in the wavelength range below 370 nm when applied to cure the sheet-form, curable pressure-sensitive adhesive. Suitably, the above photo-sensitive onium salts can be activated by the radiation in the wavelength range below 370 nm.

Also, the above-described onium salt compounds are thermally stable to advantageously enhance storage stability of the sheet-form, curable pressure-sensitive adhesive until

exposure to radiation. Furthermore, since their terminal structures for propagation are active enough to react at ambient temperature and their deactivation to stop the reaction is not expected to occur, the curing reaction both after exposure to radiation and after application to an adherend can be insured to progress.

Specifically applicable onium salt compounds include aromatic diazonium salts, aromatic iodonium salts, aromatic sulfonium salts, and pyridinium salts. The commercially available onium salt compounds which are applicable to the present invention include OPTOMER-SP-150 (manufactured by Asahi Denka kogyo Ltd.), OPTOMER-SP-151 (manufactured by Asahi Denka kogyo Ltd.), OPTOMER-SP-170 (manufactured by Asahi Denka kogyo Ltd.), OPTOMER-SP-171 (manufactured by Asahi Denka kogyo Ltd.), UVE-1014 (manufactured by General Electronics Corp.), CD-1012 (manufactured by Sartomer Corp.), SUNAID SI-60L (Sanshin Chem. Ind. Ltd.), SUNAID SL-80L (Sanshin Chem. Ind. Ltd.), SUNAID SI-100L (Sanshin Chem. Ind. Ltd.), CI-2064 (manufactured by Nippon Soda Co. Ltd.), CI-2639 (manufactured by Nippon Soda Co. Ltd.), CI-2624 (manufactured by Nippon Soda Co. Ltd.), CI-2481 (manufactured by Nippon Soda Co. Ltd.).

Lamps useful for the aforementioned irradiation can be any lamps which have a radiation distribution not exceeding 800 nm. The lamps having the radiation distribution not

2055136-013102
exceeding 370 nm may be preferably employed when the radical
photopolymerization is utilized to obtain acrylic polymers.
Examples of applicable lamps include a low-pressure mercury
vapor lamp, a moderate-pressure mercury vapor lamp, a high-
5 pressure mercury vapor lamp, an ultra high-pressure mercury
vapor lamp, chemical lamps, blacklight lamps, microwave-
exciting mercury vapor lamps, and metal halide lamps. When
it is necessary to avoid curing dominantly in a surface
layer to insure internal curing, the irradiation may be
10 applied with a wavelength region not exceeding 300 nm being
excluded.

Mixing Proportions

In the present invention, the mixing proportions of the
high molecular weight polymer (A), the compound (B)
15 containing an epoxy group and the polymerization initiator
(C) are not particularly limited, as long as the adequate
tackiness of the sheet-form, curable pressure-sensitive
adhesive and the adequate adhesive strength thereof after
the activation energy application are insured to be
20 obtained. However, it is preferred to add 1-10000 parts by
weight of the compound containing an epoxy group and 0.01-
1000 parts by weight of the polymerization initiator (C) per
100 parts by weight of the high molecular weight polymer.

If the mixing proportion of the compound containing an
25 epoxy group is below 1 part by weight, in some cases,

inadequate adhesive strength may result when the activation energy is applied to cure the compound containing an epoxy group. As it goes beyond 10000 parts by weight, the relative proportion of the high molecular weight polymer (A) becomes smaller so that inadequate tackiness may result. On the other hand, if the mixing proportion of the polymerization initiator (C) falls below 0.01 parts by weight, it becomes difficult in some instances to fully polymerize the compound (B) containing an epoxy group even upon application of the activation energy. As it exceeds 1000 parts by weight, the relative proportion of the polymerization initiator becomes excessively larger to possibly cause the epoxy consumption to proceed rapidly upon exposure to a light so that curing is almost completed before combining adherends to provide poor adhesion. This results in reduced tackiness and adhesive strength after curing.

When the aforementioned vinyl ether compound is additionally incorporated in accordance with the present invention, it is preferred to add 30-70 parts by weight of the compound (B), 1-30 parts by weight of the vinyl ether compound, and 0.01-10 parts by weight of the cationic photopolymerization initiator.

If the mixing proportion of the compound containing an epoxy group is below 30 parts by weight, the inherent

adhesive strength of the epoxy resin may not be fully
imparted even if curing should occur. If it exceeds 70
parts by weight, a reduced cohesive strength of the sheet-
form, curable pressure-sensitive adhesive possibly results
5 so that its pressure-sensitive adhesion to an adherend may
become difficult. Accordingly, an improved workability may
not be expected.

On the other hand, if the mixing proportion of the
vinyl ether compound is below 1 part by weight, curing may
10 become substantially comparable to that of the vinyl ether
compound sole. If it goes beyond 30 parts by weight, a
reduced strength of a photocured substance possibly results
so that adequate adhesive strength may not be obtained.

If the mixing proportion of the cationic photoinitiator
15 falls below 0.01 parts by weight, a resulting concentration
of the cationically polymerizable species possibly becomes
too low to increase a curing speed to a suitable level. If
it is greater than 30 parts by weight, curing progresses
rapidly at a surface of the sheet-form, curable pressure-
20 sensitive adhesive to possibly prevent an adhesive surface
of the same from intimately contacting with an adherend,
even if the vinyl ether compound is included as one
component. This may result in its inadequate adhesive
strength, although an ultimate mechanical strength may be
25 adequately given to the cured substance. In the above-

described preferred formulation, the mixing proportion of the cationic photoinitiator is more preferably from 0.05 to 5 parts by weight, still more preferably in the range of 0.1 to 3 parts by weight.

5 As to incorporation of the acrylic polymer, 30-70 parts by weight of the acrylic polymer is preferably added to 30-70 parts by weight of the compound containing an epoxy group, 1-30 parts by weight of the vinyl ether compound and 0.01-10 parts by weight of the cationic photoinitiator. If
10 the mixing proportion of the acrylic polymer is below 30 parts by weight, a reduced cohesive strength of the sheet-form, curable pressure-sensitive adhesive may result to possibly prevent the pressure-sensitive adhesion thereof to the adherend so that an improved workability may not be
15 attained. If it is greater than 70 parts by weight, the inherent adhesion of the epoxy resin may not be expected in some instances.

Other Additives

 When necessary to improve cohesive strength at an
20 elevated temperature and/or heat resistance, the sheet-form, curable pressure-sensitive adhesive in accordance with the present invention may further contain, if desired, one or more of such curable monomers as polyfunctional acrylate monomers and polyfunctional vinyl monomers in suitable
25 proportions which will not otherwise adversely affect the

purpose of the invention.

Examples of the curable monomers include, but not limited to, hexane diol di(meth)acrylates, ethylene glycol di(meth)acrylates, polyethylene glycol di(meth)acrylates, propylene glycol di(meth)acrylates, polypropylene glycol di(meth)acrylates, neopentyl glycol di(meth)acrylates, trimethylolpropane tri(meth)acrylates, pentaerythritol di(meth)acrylates, pentaerythritol tri(meth)acrylates, pentaerythritol tetra(meth)acrylates, dipentaerythritol hexa(meth)acrylates, epoxy acrylates, polyester acrylates, urethane acrylates and any suitable combinations thereof.

In addition to the tack polymer, the compound containing an epoxy group and the cationic photoinitiator, the sheet-form, curable pressure-sensitive adhesive in accordance with the present invention may further contain known tackifying resins and/or extenders in suitable proportions which will not otherwise adversely affect the purposes of the invention.

For example, such tackifying resins as rosin resins, modified rosin resins, terpene resins, terpene phenol resins, aromatic modified terpene resins, C5 or C9 type petroleum resins, and chroman resins may be added for the purpose of improving tackiness of the sheet-form, curable pressure-sensitive adhesive.

In a particular case where an adherend is of

polyolefins, the use of rosin or petroleum resins is preferred for its ability to provide strong adhesion.

Also, thickeners such as acrylic rubbers, epichlorhydrin rubbers, isoprene rubbers, and butyl rubbers; 5 thixotropic agents such as colloidal silica and poly(vinyl pyrrolidone); extenders including calcium carbonates, titanium oxides, clays and the like; and the others may further be added in an attempt to improve coatability of the composition.

10 For the purpose of providing the sheet-form, curable pressure-sensitive adhesive with high shear bond strength, further added may be inorganic balloons such as glass balloons, alumina balloons, and ceramic balloons; organic spheres such as nylon beads, acrylic beads, and silicone 15 beads; organic balloons such as vinylidene chloride balloons and acrylic balloons; monofibers such as of glass, polyester, rayon, nylon, cellulose and the others; and the others.

While possible to add glass fibers in fibrous chip form 20 to the composition, it is preferred to impregnate glass woven fibers with the aforementioned photopolymerizable composition to impart increased shear bond strength.

Preparation of the Sheet-Form, Curable Pressure-Sensitive Adhesives

25 The sheet-form, curable pressure-sensitive adhesive in

accordance with the present invention may be prepared by any suitable means known in the art, such as solvent coating, extrusion coating, calendering, UV polymerization.

10059136-013102
5 In accordance with the solvent coating process, an organic solvent dissolves the tack polymer, the compound containing an epoxy group, the polymerization initiator and, if necessary, the vinyl ether compound before it is coated on a base material and subsequently dried to form a sheet. The extrusion coating or calendering is a process wherein a
10 composition is heat melted which includes a hot-melt tack polymer having a weight average molecular weight of from about several tens thousands to about 0.5 million, the compound containing an epoxy group, the cationic photoinitiator, and, if necessary, the vinyl ether compound.
15 The melted composition is coated on a base material by means of a melt coating equipment.

For an exemplary purpose, one preferred embodiment of the process for preparing the sheet-form, curable pressure-sensitive adhesive in accordance with the present invention
20 is hereinafter described utilizing the above-mentioned UV polymerization process. In this preferred embodiment, a photopolymerizable composition is employed which includes a radical photoinitiator capable of being activated by irradiation in a different wavelength region from those
25 respective regions for (meth)acrylate monomers and photo-

2054136-013103
sensitive onium salt compound, the compound containing an epoxy group, the vinyl ether compound if necessary, and the photo-sensitive onium salt compound. The sheet-form, curable pressure-sensitive adhesive can be obtained by coating photopolymerizable composition on a suitable substrate sheet, and photoactivating only the radical photoinitiator to cause a radical polymerization to dominantly take place so that an acrylic polymer as the tack polymer is formed on the substrate sheet.

10 In such a process utilizing the photopolymerizable composition, the acrylic polymer as the tack polymer can be obtained by irradiation with a light.

In the above preferred embodiment, suitable photo-sensitive onium salt compound and radical photoinitiator may be selected in a more preferable manner so that the photo-sensitive onium salt compound is little photoactivated by a radiation in a wavelength region equal to and greater than 370 nm while the radical photoinitiator is photoactivated by a radiation in a wavelength region equal to and greater than 370 nm but below 800 nm. Accordingly, the sheet-form, curable pressure-sensitive adhesive can be obtained by irradiation in a wavelength region from 370 nm to 800 nm.

If the irradiation used in the preparation has a wavelength equal to or greater than 800 nm, radiation heat acts to degrade the sheet-form, curable pressure-sensitive

adhesive, which accordingly necessitates additional provisions such as of a heat radiation cut filter or other heat removing facilities. On the contrary, such a need is eliminated if the photoinitiator is used which can be
5 photoactivated by irradiation in a wavelength region below 800 nm as described above.

The irradiation in a wavelength of less than 370 nm activates the photo-sensitive onium salt compound so that the sheet-form, curable pressure-sensitive adhesive of the
10 present invention can not be obtained. In view of such a disadvantage, the radical photoinitiator is preferably used which is capable of being photoactivated by irradiation in a wavelength region equal to and greater than 370 nm but below 800 nm as described above.

As can be appreciated from the above description, the
15 370 nm wavelength is regarded as bounding the spectrum into two different wavelength regions; the wavelength region suitable for photoactivating the photo-sensitive onium salt compound and the wavelength region suitable for
20 photoactivating the radical photoinitiator. Accordingly, the selective use of different light sources having their respective output spectral patterns enables readily providing different radiations having their respective wavelength regions, i.e., one radiation having the
25 wavelength region equal to or greater than 370 nm and

another radiation having the wavelength region below 370 nm.

Since it needs a higher energy to induce ring-opening of the epoxy linkages than required for inducing the radical photopolymerization, it is desirable that the radical photopolymerization is effected by irradiation in the wavelength region equal to or greater than 370 nm while the irradiation in the wavelength region below 370 nm is used to initiate the cationic photopolymerization to allow the ring-opening reaction of the epoxy linkages to take place.

The radical photoinitiator as described above as being photoactivated by irradiation in a wavelength region equal to or greater than 370 nm is the compound which must be photoactivated by irradiation of a light in a wavelength region equal or and greater than 370 nm, and which preferably does not permit an energy to be transferred to the cationic photoinitiator when received a radiation in a wavelength region below 370 nm. Suitable examples of such a radical photoinitiator include acetophenone derivative compounds such as 4-(2-hydroxyethoxy)phenyl(2-hydroxy-2-propyl)ketone, α -hydroxy- α, α' -dimethylacetophenone, methoxyacetophenone, 2,2-dimethoxy-2-phenylacetophenone; benzoin ether compounds such as benzoin ethyl ether, benzoin isopropyl ether; ketal derivative compounds such as benzyldimethyl ketal; ketone halides; acylphosphine oxides; acylphosphonates; and bis-(2,6-dimethoxybenzoyl)-2,4,4-

trimethylpentyl phosphine oxides.

Of the above photoinitiators, particularly preferred are acylphosphine oxides, acylphosphonates, and bis-(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxides which show high levels of adsorption index to a light in a wavelength region exceeding 370 nm.

Examples of lamps useful for irradiation in the practice of the radical photopolymerization include a low-pressure mercury vapor lamp, a moderate-pressure mercury vapor lamp, a high-pressure mercury vapor lamp, an ultra high-pressure mercury vapor lamp, chemical lamps, blacklight lamps, microwave-exciting mercury vapor lamps, metal halide lamps and fluorescent lamp.

The Curable Pressure-Sensitive Adhesive Members

The sheet-form, curable pressure-sensitive adhesive in accordance with the present invention may be employed as a double-sided pressure-sensitive adhesive tape which, when in use, is interposed between two adherends for joining thereof. Alternatively, the sheet-form, curable pressure-sensitive adhesive may be placed on at least one surface of a substrate to form a curable pressure-sensitive adhesive sheet.

Suitable substrates for such a sheet include, but not limited to, non-woven fabrics such as of rayons and celluloses; plastic films or sheets made of synthetic resins

such as polyethylene, polyester, cellophane, polypropylene, polystyrene, and polyimido; foams such as polyethylene foams, urethane foams, neoprene foams, vinyl chloride foams, and polystyrene foams; plastic plates made of synthetic resins such as polystyrene, ABS, acrylics, polypropylene, and polyethylene; metallic sheets or plates such as of steel, stainless steel, copper, aluminium; glasses; woods; papers; clothes; tiles; plaster boards; and calcium silicate insulator.

10 Any shaped substrates may be employed, without limited to those having small thickness dimensions such as in a sheet or plate form, examples of which include square columns, rods, spheres, those having nonspherical surfaces.

Procedures for Joining Adherends

15 Where two adherends are joined together by means of the sheet-form curable pressure-sensitive adhesive of the present invention, an activation energy is applied to cure the sheet-form curable pressure-sensitive adhesive either before or after the adherends are combined via the same.

20 The expression "before the adherends are combined" as used herein is intended to mean literally before the adherends are combined and in effect before the curing of resins containing an epoxy group through application of the activation energy is completed. When the curing of the
25 compound containing an epoxy group through the activation

energy application is completed, the sheet-form curable pressure-sensitive adhesive possibly becomes too stiff to provide adequate initial tackiness.

5 If the sheet-form curable pressure-sensitive adhesive is, prior to joining the adherends, irradiated with a light as the activation energy to allow the curing thereof to progress, at least one adherend does not receive the irradiation so that photodegradation or photo-deterioration thereof can be avoided. Thus, it is desirable to irradiate
10 the sheet-form curable pressure-sensitive adhesive prior to joining the adherends which are likely to be degraded or deteriorated by irradiation. In a particular case where one adherend is easy to degrade or deteriorate upon exposure to irradiation while another adherend is difficult, the sheet-
15 form curable pressure-sensitive adhesive may be first combined with the another adherend, followed by the irradiation, and is subsequently combined with the one adherend.

As to a wavelength of irradiation for photocuring, when
20 the photo-sensitive onium salt compound is used as the cationic photoinitiator, it is preferable to utilize the irradiation in a wavelength region equal to and greater than 300 nm and having an intensity from 1 mW/cm² to 100 mW/cm², preferably from 5 mW/cm² to 100 mW/cm². The radiation having
25 a wavelength below 300 nm is able to provide a sufficient

activation energy for activating the photo-sensitive onium salt compound, however, its transmittance is insufficient such that only the tacky surface of the sheet-form curable pressure-sensitive adhesive may be crosslinked. This possibly prohibits an intimate contact of the sheet-form curable pressure-sensitive adhesive surface with the adherends. In some instances, an interior of the sheet-form curable pressure-sensitive adhesive remains uncured.

If the radiation in a wavelength region equal to and greater than 300 nm has an intensity of below 1 mW/cm², its energy is insufficient to activate the photo-sensitive onium salt compound so that only a small proportion thereof is photoactivated. This results in a reduced curing speed. From the foregoing, a useful radiation preferably has a wavelength of at least 300 nm, more preferably at least 300 nm but below 800 nm, still more preferably at least 300 nm but below 400 nm.

On the other hand, if the irradiation intensity goes beyond 100 mW/cm², radiation heat reaches a substantial level to promote the cure reaction. Accordingly, the adherends must be combined together immediately after the irradiation, i.e., prior to a rapid surface curing of the sheet-form, curable pressure-sensitive adhesive. Otherwise, an intimate contact of the sheet-form curable pressure-sensitive adhesive with the adherend may not be attained.

DESCRIPTION OF THE PREFERRED EXAMPLES

EXAMPLE 1

10059136-013102
5 A separable flask was charged with 70 g of 2-ethylhexyl
acrylate, 30 g of N-vinyl pyrrolidone, 2 g of CYCLOMER
(manufacture by Daicel Chemical Industries Ltd.) as an
epoxy-containing (meth)acrylate monomer, 50 g of EPICOAT 828
(manufactured by Yuka-Shell Epoxy Co.), 0.05 g of bis(2,6-
dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide as a
radical photopolymerization initiator, 0.5 g of OPTOMER SP-
10 170 (manufactured by Asahi Denka Kogyo Ltd.) as a cationic
photopolymerization initiator. The mixture was stirred in
the flask to insure complete homogeneity thereof, and was
thereafter purged with nitrogen gas to remove dissolved
oxygen, thereby obtaining a photopolymerizable composition.

15 The photopolymerizable composition obtained was coated
on a release surface of a transparent PET [poly(ethylene
terephthalate)] film to a thickness of 300 μ m. Another
transparent PET film also having a release surface was
laminated onto the coated composition so as to face its
20 release surface toward the composition. As a result, the
coated photopolymerizable composition was flanked by the
pair of transparent PET films to form a laminate. The
laminate was irradiated from above with a fluorescent lamp
emitting a radiation having a maximum wavelength of 400 nm
25 so that the composition was exposed via one of the

transparent PET films to a near ultraviolet light which substantially excluded a radiation in the wavelength range below 370 nm. The near ultraviolet irradiation was continued at an intensity of 6 mW/cm² for 5 minutes to form a sheet-form, curable pressure-sensitive adhesive sheet flanked between the pair of transparent PET films. During the irradiation, an intensity of the irradiation in the wavelength range below 370 nm was found to be 0.001 mW/cm².

A T-peel strength and an overlap shear stress of the sheet-form, curable pressure-sensitive adhesive obtained were respectively measured at room temperature in accordance with JIS Z 0237 to reveal 0.4 kgf/cm and 2.5 kgf/cm² with use of stainless steel as adherend, respectively.

The sheet-form, curable pressure-sensitive adhesive flanked between the pair of transparent PET films was exposed for 60 seconds to an ultraviolet light having an intensity of 25 mW/cm² in the wavelength range below 370 nm, using an ultra high-pressure mercury vapor lamp capable of emitting a radiation with a maximum wavelength at 365 nm. At least one of the pair of transparent PET films was removed from the laminate to subsequently adhere an exposed surface of the coated composition to an adherend. The T-peel strength and overlap shear stress immediately after the adhesion were measured at room temperature to be 0.5 kgf/cm

and 2.6 kgf/cm² with use of stainless steel as adherend, respectively. Those values after they had been left overnight were 3 kgf/cm and 15 kgf/cm², respectively.

Also, the sheet-form, curable pressure-sensitive adhesive flanked between the pair of transparent PET films was cut into a 20 mm by 20 mm strip. One of the transparent PET film was removed from the strip which was then on its adhesive surface backed by a stainless steel foil. The sheet-form, curable pressure-sensitive adhesive was exposed through the remaining transparent PET film to a near ultraviolet light in the same manner as described above. The remaining transparent PET film was then peeled for removal from the sheet-form, pressure-sensitive adhesive which was subsequently on its exposed surface adhered to a stainless steel plate so that the sheet-form, curable pressure-sensitive adhesive was flanked between the stainless steel foil and plate. A weight was suspended from the stainless steel plate to apply a load of 1 kgf in a shear direction at 100 °C. The weight did not fall even in 24 hours after application of the load.

EXAMPLE 2

A sheet-form, curable pressure-sensitive adhesive was obtained in the same manner as described in Example 1, except that 5 g of glass fiber chips was added to the photopolymerizable composition of Example 1.

10059136 "013102
A T-peel strength and an overlap shear stress of the sheet-form, curable pressure-sensitive adhesive obtained were respectively measured at room temperature in accordance with JIS Z 0237 to reveal 0.3 kgf/cm and 6 kgf/cm² with use of stainless steel as adherend, respectively.

The sheet-form, curable pressure-sensitive adhesive was irradiated with an ultraviolet light in the same manner as practiced in Example 1 and then adhered to an adherend. The T-peel strength immediately after adhesion were 3 kgf/cm and the overlap shear stress exceeded 18 kgf/cm².

EXAMPLE 3

A sheet-form, curable pressure-sensitive adhesive flanked between the pair of transparent PET films was obtained in the same manner as practiced in Example 1, except that epoxy-containing (meth)acrylate monomers were not used.

A T-peel strength and an overlap shear stress of the sheet-form, curable pressure-sensitive adhesive obtained were respectively measured at room temperature in accordance with JIS Z 0237 to reveal 0.45 kgf/cm and 4.5 kgf/cm² with use of stainless steel as adherend, respectively.

One of the transparent PET film was peeled for removal from the sheet-form, curable pressure-sensitive adhesive which was subsequently on its exposed surface adhered to an adherend. The sheet-form, curable pressure-sensitive

adhesive was exposed via the remaining transparent PET film to a radiation having an intensity of 25 mW/cm² for 30 seconds, using an ultra high-pressure mercury vapor lamp which had a emitting radiation with a maximum wavelength at 365 nm. The remaining transparent PET film was removed from the sheet-form adhesive which was subsequently on its exposed surface adhered to another adherend.

The T-peel strength and overlap shear stress immediately after the adhesion were 0.6 kgf/cm and 4.5 kgf/cm², respectively. Those values after they had been left overnight were 3.5 kgf/cm and 15 kgf/cm², respectively.

Also, the sheet-form, curable pressure-sensitive adhesive flanked between the pair of transparent PET films was cut into a 20 mm by 20 mm strip. One of the transparent PET film was peeled for removal from the sheet-form, curable pressure-sensitive adhesive which was then on its exposed surface backed by a stainless steel foil. The sheet-form, curable adhesive was exposed through the remaining transparent PET film to an ultraviolet light in the same manner as practiced in Example 1. The remaining transparent PET film was peeled for removal from the irradiated sheet-form adhesive which was then on its exposed surface adhered to a stainless steel plate so that the sheet-form adhesive was flanked between the stainless steel foil and plate. A weight was suspended from the stainless steel plate to apply

a load of 1 kgf in a shear direction at 100 °C. The weight fell in 5 minutes after application of the load.

EXAMPLE 4

Into a 0.5 L separable flask was charged 30 g of
5 glycidyl methacrylate, 90 g of epoxy resin (manufactured by Yuka-Shell Epoxy Corp.; product name: EPICOAT 828), 10 g of cyclohexanedimethanol divinyl ether (manufactured by ISP Corp.), 0.1 g of bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide (manufactured by Chiba Geigy;
10 product name: IRGACURE 1700) as a radical photoinitiator, 0.5 g of a cationic photoinitiator (manufacture by Asahi Denka Kogyo Ltd.; product name: OPTOMER SP-170). The mixture was stirred in the flask to insure complete homogeneity thereof, followed by bubbling a nitrogen gas
15 therethrough to remove dissolved oxygen, to obtain a photopolymerizable composition.

The photopolymerizable composition obtained was coated on a release surface of a transparent PET (polyethylene terephthalate) film to a thickness of 300 μm. Another
20 transparent PET film having a release surface was laminated onto the coated composition so as to face its release surface toward the composition. As a result, a coated photopolymerizable composition was flanked by the pair of transparent PET films to form a laminate. The laminate was
25 irradiated with a fluorescent lamp emitting a radiation

having a maximum wavelength of 400 nm so that the composition was exposed via at least one of the transparent PET films to a near ultraviolet light which substantially excluded a radiation in the wavelength range below 370 nm.

5 The near ultraviolet irradiation was continued at an intensity of 1 mW/cm² for 10 minutes to obtain a sheet-form, curable pressure-sensitive adhesive present between the pair of transparent PET films.

EXAMPLES 5-9 and COMPARATIVE EXAMPLES 1 and 2

10 In Examples 5-9 and Comparative Examples 1 and 2, respective sheet-form, curable pressure-sensitive adhesives flanked between the pair of transparent PET films were obtained in the same manner as practiced in Example 4, except that the photopolymerizable compositions as employed
15 in respective Examples included different types and/or amounts of components, with the exception of the radical photoinitiator consistently employed throughout Examples, as listed in the following Table 1.

Evaluations of EXAMPLES 4-9 and COMPARATIVE EXAMPLES 1 and 2

20

I. Evaluation of Overlap Shear Strength Immediately After Irradiation

One of the transparent PET film was removed from the laminate which was then cut into a 25 mm x 25 mm laminate
25 strip. The strip was on its adhesive surface adhered onto a

period after irradiation. The time period can be considered to be within a pot life, provided that its corresponding overlap shear strength value as herein measured is comparable to that measured in the above evaluations wherein the adhesion to the adherend B was effected immediately after irradiation. Accordingly, a maximum time period from irradiation till adhesion to the adherend B was determined as a pot life when an overlap shear strength value corresponding to the time period approximately reached a corresponding overlap shear strength value obtained in the above evaluations of overlap shear strength immediately after irradiation. The results are also shown in Table 1.

Table 1

		Example 4	Example 5	Example 6	Example 7	Example 8	Example 9	Comparative Example 1	Comparative Example 2
Compound Containing an Epoxy Group [Parts by Weight]	Epoxy Resin 1	90	80	65	60	65	60	100	70
	Epoxy Resin 2			30	30	30	30		30
Vinyl Ether Compound [Parts by Weight]	Cyclohexane Dimethanol Divinyl Ether	10	20	5	10				
	Triethyl-ene Glycol Methyl Vinyl Ether					5	10		
Photo-sensitive Onium Salt [Parts by Weight]	SP-170	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
	Glycidyl Methacrylate	30	30	30	30	30	30	30	30
Overlap Shear Strength Immediately After Irradiation(kgf/cm ²)		15.7	15.9	24.3	17.4	21	12	11.6	30.4
Pot Life [Minutes]		30	60	120	60	120	120	10	30

In Table 1, "Epoxy resin 1" and "Epoxy resin 2" indicate EPICOAT 828 (product name) manufactured by Yuka-Shell Epoxy Corp. and RIKARESIN BEO-60E (product name) manufactured by New Japan Chemical Co., Ltd., respectively. Also, "cyclohexanedimethanol divinyl ether" and "triethylene glycol methylvinyl ether" are products manufactured by ISP TECHNOLOGIES, INC. and BASF, respectively.

EXAMPLE 10

Into a 2 L separable flask is charged 50 g the above-mentioned compound 2 (manufactured by Daicel Chem. Ind. Ltd.; product name: PLACCEL FM-2D; n=2), 150 g of glycidyl methacrylate, 300 g of epoxy resin (manufactured by Yuka-Shell Epoxy Corp.; product name: EPICOAT 828), 150g of epoxy resin (manufactured by New Japan Chemical Co., Ltd.; product name: RIKARESIN BEO-60E), 0.5 g of bis(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide (manufactured by Chiba Geigy; product name: IRGACURE 1700) as a radical photoinitiator, and 2.5 g of a cationic photoinitiator (manufacture by Asahi Denka Kogyo Ltd.; product name: OPTOMER SP-170). The mixture was stirred in the flask to insure complete homogeneity thereof, followed by bubbling a nitrogen gas therethrough to remove dissolved oxygen, to obtain a photopolymerizable composition.

The photopolymerizable composition obtained was coated on a release surface of a transparent PET [poly(ethylene

terephthalate)] film to a thickness of 0.3 mm. Another transparent PET film also having a release surface was laminated onto the coated composition so as to face its release surface toward the composition. Thus, the coated photopolymerizable composition was flanked by the pair of transparent PET films to form a laminate.

The laminate was irradiated with a fluorescent lamp emitting a radiation having a maximum wavelength of 400 nm so that the coated composition was exposed via at least one of the transparent PET films to a near ultraviolet light which substantially excluded a radiation in the wavelength range below 370 nm. The near ultraviolet irradiation was continued at an intensity of 1 mW/cm² for 10 minutes to obtain a sheet-form, curable pressure-sensitive adhesive present between the pair of transparent PET films.

EXAMPLES 11-28 and COMPARATIVE EXAMPLES 3-10

In Examples 11-28 and Comparative Examples 3-10, respective sheet-form, curable pressure-sensitive adhesives flanked between the pair of transparent PET films were obtained in the same manner as practiced in Example 10, with the exceptions that the photopolymerizable compositions as employed in respective Examples were altered as listed in the following Tables 2-5.

In addition, the details of product name shown in Tables 2-5 are as follows;

207EFD" 9ET6500T

(1) PLACCEL FM-2D *** manufactured by Daicel Chem. Ind.
Ltd., and corresponds to the above
mentioned compound 2, $n=2$.

5 (2) PLACCEL FM-1D *** manufactured by Daicel Chem. Ind.
Ltd., and corresponds to the above
mentioned compound 2, $n=1$.

10 (3) PLACCEL FM-5D *** manufactured by Daicel Chem. Ind.
Ltd., and corresponds to the above
mentioned compound 2, $n=5$.

15 (4) BLENMER PP-500 *** manufactured by Nippon Oil & Fats
Co., Ltd. and corresponds to the
above mentioned compound 6, $n=9$.

(5) ADEKARESIN EP-4901 *** manufactured by Asahi Denka
Kogyo Ltd., epoxy resin.

20 (6) ADEKARESIN EP-4080 *** manufactured by Asahi Denka
Kogyo Ltd., epoxy resin.

(7) SELOKISAIDO 2081 *** manufactured by Daicel Chem.
Ind. Ltd., epoxy resin.

Evaluation of EXAMPLES 11-28 and COMPARATIVE EXAMPLES 3-10

Evaluation of Overlap Shear Strength

2059136-01102
2070736-01102

One of the transparent PET film was removed from the laminate which was then cut into a 25 mm x 25 mm laminate strip. The strip was on its adhesive surface adhered onto a stainless steel plate (SUS 304, hereinafter referred to as an adherend A) which was 25 mm in width, 150 mm in length, and 2 mm in thickness. The stainless steel plate was abraded by a water-resistant abrasive paper # 280, degreased at its surface with ethyl acetate, and dried. Subsequently, the laminate was irradiated with a light having an intensity of 30 mW/cm² in a wavelength region from 300 nm to 370 nm such that the sheet-form, curable pressure-sensitive adhesive was exposed through the remaining transparent PET film to the light for 30 seconds.

Immediately after the irradiation, the remaining transparent PET film covering a back surface of the sheet-form composition was removed from the laminate to adhere an exposed surface of the sheet-form composition to an adherend B which was prepared in the same manner as the adherend A. As a result, a test piece for overlap shear strength measurement was prepared which included the sheet-form, pressure-sensitive adhesive composition joining the adherends A and B.

After the joint of the adherends A and B, the above test piece was aged for 7 days before its overlap shear strength was measured at a stress speed of 10 mm/min in accordance with JIS K 6850 and Z 0237. The results are given in the following Tables 2-5.

Evaluation of Complete Finish Time of Curing

A test piece for shear bond strength measurement was obtained in the same manner as described in the above evaluations of shear bond strength. The test piece was measured for its shear bond strength at a stress speed of 10 mm/min according to JIS K 6850 and Z 0237 at predetermined time intervals after irradiation. Assuming that the overlap shear strength value approximately reached an ultimate value when the measured overlap shear strength became to be approximately equal to the value after aging of 7 days in the above evaluation of overlap shear strength, the time period was determined as a complete finish time of curing.

Table 2

		Example				Comparative Example
		10	11	12	13	
Acrylic Monomer	Compound 2, n=2, PLACCEL FM-2D	10	20	40	60	
Copolymerizable Monomer	Glycidyl Methacrylate	30	30	30	30	30
Compound Containing an Epoxy Group	EPICOAT 828	60	50	30	10	70
	RIKARESIN BEO-60E	30	30	30	30	30
Radical Photoinitiator	IRGACURE 1700	0.1	0.1	0.1	0.1	0.1
Cationic Photoinitiator	OPTOMER SP-170	0.5	0.5	0.5	0.5	0.5
SUS Overlap Shear Strength (kgf/cm ²)		41	53	65	53	25
Complete Finish Time of Curing (Hours)		72	72	120	120	170

[All Mixing Proportions are indicated by Parts by Weight]

Table 3

	Example		Comparative Example
	14	15	
Acrylic Monomer	10	20	
Copolymerizable Monomer	30	30	30
Compound Containing an Epoxy Group	40	30	50
Radical Photoinitiator	20	20	20
Cationic Photoinitiator	0.1	0.1	0.1
SUS Overlap Shear Strength (kgf/cm ²)	0.5	0.5	0.5
Complete Finish Time of curing (Hours)	60	62	44
	140	120	170

[All Mixing Proportions are indicated by Parts by Weight]

Table 4-1

	Example		Comparative Example
	16	17	
Acrylic Monomer	10	20	
Copolymerizable Monomer	30	30	30
Compound Containing an Epoxy Group	40	20	50
Radical Photoinitiator	0.1	0.1	0.1
Cationic Photoinitiator	0.5	0.5	0.5
SUS Overlap Shear Strength (kgf/cm ²)	80	90	59
Complete Finish Time of Curing (Hours)	24	24	48

[All Mixing Proportions are indicated by Parts by Weight]

Table 4-2

	Example 18	Compar- ative Example 6	Example 19	Compar- ative Example 7	Example 20	Compar- ative Example 8	Example 21	Compar- ative Example 9
Acrylic Monomer	20		20		20		20	
Copolymeriza- ble Monomer		20		20		20		20
n-Butyl Acrylate	30	30	30	30	30	30	30	30
Tetrahydrofurfuryl Acrylate								
EPICOAT 828	50	50						
RIKARESIN BEO-60E								
ADEKARESIN EP-4901			50	50				
ADEKARESIN EP-4080					50	50		
SELOKISAIDO 2081 (Alicyclic)							50	50
IRGACURE 1700	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Radical Photoinitiator								
OPTOMER SP-170	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Cationic Photoinitiator								
SUS Overlap Shear Strength (kgf/cm ²)	60	25	70	32	95	25	75	30
Complete Finish Time of Curing (Hours)	24	48	24	36	24	36	12	24

[All Mixing Proportions are indicated by Parts by Weight]

Table 5

		Example							Comparative Example
		22	23	24	25	26	27	28	
Acrylic Monomer	4-Hydroxybutyl Acrylate	20							
	2MHP*		20						
	Compound 2, n=1, PLACCEL FM-1D			20					
	Compound 2, n=2, PLACCEL FM-2D				20			50	
	Compound 2, n=5, PLACCEL FM-5D					20			
	Compound 6, n=9, BLENNER PP-500						20		
Copolymerizable Monomer	Tetrahydrofurfuryl Acrylate	30	30	30	30	30	30		50
Compound Containing an Epoxy Group	EPICOAT 828	30	30	30	30	30	30	30	30
	RIKARESIN BEO-60E	20	20	20	20	20	20	20	20
Radical Photoinitiator	IRGACURE 1700	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Cationic Photoinitiator	OPTOMER SP-170	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
SUS Overlap Shear Strength (kgf/cm ²)		65	40	75	95	70	80	90	38
Complete Finish Time of Curing (Hours)		12	24	12	36	24	24	24	48

[*••••2-Methacryloyloxyethyl-2-Hydroxypropyl Phthalate]

[All Mixing Proportions are indicated by Parts by Weight]